TECHNICAL DATASHEET

Product description	
Colour	Black
Fibre composition	PET
Fibre bonding	Thermobonded
Product treatment	Impregnated
Intended use	Filtration

Product specification				
Characteristic	Test method	Unit	Nominal value	Tolerance
Mass per unit area	EN ISO 9073-1	g/m²	240	± 35
Thickness at 0,5 kPa	EN ISO 9073-2	mm	2.4	± 0.5
Air permeability at 200 Pa	EN ISO 9237	l/m²/s	2200	± 350
Flammability (MD/CD)	DIN 53 438, part2	-	-	K1
Flammability (MD/CD)	DIN 53 438, part3	-	-	F1

MD: Machine direction
CD: Cross direction
Tolerance of width is ± 20 mm.

Laboratory tests are carried out on non-conditioned samples in non-conditioned testing environment. Testing conditions do not influence the results accuracy.

This material was designed for sorption of smell. Content of activated carbon is avg. 29 %.

Above technical values are based on an average of running production.

AZ SERVIZI GENERALI SRL
Sede Legale: Via L. Einaudi 1/B, 30036 Santa Maria Di Sala (VE)
Sede Amministrativa: Via Bonisiolo 16/B, 31021 Mogliano Veneto (TV)
Sede Logistica/Operativa: Via S. Merli 56, 29121 Piacenza

SERVIZI GENERALI